

WBMPCSB

SKC Window Film

Advantage -

1. Increase personal privacy
2. Better eye comfort
3. Great maintenance with less scratch
4. Long life indoor fabric from fading

Clear Hard-Coating

Metallizing Film (12±1μm)

Adhesive

Optical Grade PET Film (23±1μm)

UV-Cut PSA

Silicone Release Film(23μm)

| | | | |
|------------------------------------|-------------|-------|-----------------------|
| Visible Light Transmitted | | 10% | KS L 2016 ISO 9050 |
| Visible Light Reflected | External | 20.7% | KS L 2016 ISO 9050 |
| | Internal | 56.5% | |
| Solar Heat Reduction | | 67% | KS L 2016 |
| Solar Heat | Reflected | 28% | ISO 9050 |
| | Absorbed | 62.3% | |
| | Transmitted | 9.7% | |
| IR Transmitted | | 9% | ISO 9050 |
| UV Rejected | | 99%↑ | KS L 2514 ISO 9050 |
| Total Solar Energy Rejected (TSER) | | 76% | ISO 9050 |

| | | |
|------------------------------------|---------------------|------------|
| Thickness | 1.5Mil/2Ply | |
| Shading Coefficient | 0.33 | KS L 2016 |
| Solar Heat Gain Coefficient (SHGC) | 0.28 | KS L 2514 |
| Scratch Resistant | >2H | ASTM D3363 |
| Haze | 1.5% | ASTM D1003 |
| Adhesion of Hard-Coated Surface | 5B (0% peel-off) | ASTM D3359 |