

WVC18CG

SKC Window Film

Advantage -

1. Increase personal privacy
2. Better eye comfort
3. Great maintenance with less scratch
4. Long life indoor fabric from fading

Clear Hard-Coating

Chip-Dyed PET Film (23±1μm)

UV-Cut PSA

Silicone Release Film(23μm)

Visible Light Transmitted		13%	KS L 2016 ISO 9050
Visible Light Reflected	External	4.4%	KS L 2016 ISO 9050
	Internal	4.5%	
Solar Heat Reduction		31%	
Solar Heat	Reflected	5.7%	ISO 9050
	Absorbed	51.2%	
	Transmitted	43.1%	
IR Transmitted		80%	ISO 9050
UV Rejected		99%↑	KS L 2514 ISO 9050
Total Solar Energy Rejected (TSER)		43.4%	ISO 9050

Thickness	1Mil/1Ply	
Shading Coefficient	0.69	KS L 2016
Solar Heat Gain Coefficient (SHGC)	0.64	KS L 2514
Scratch Resistant	>2H	ASTM D3363
Haze	0.5%	ASTM D1003
Adhesion of Hard-Coated Surface	5B (0% peel-off)	ASTM D3359